

[illegible]

2. The article of claim 1 wherein the thiuram compound is tetrabenzyl thiuram disulfide.

4. The article of claim 1 wherein the thiuram compound is present in a concentration range of between about 0.45 parts per 100 parts of polyisoprene and about 0.75 parts per 100 parts of polyisoprene.

6. The article of claim 1 wherein the second compound is zinc dibenzylidithiocarbamate.

7. The article of claim 6 wherein the zinc dibenzylidithiocarbamate is present in a concentration range of between about 0.3 parts per 100 parts of polyisoprene and about 0.5 parts per 100 parts of polyisoprene.

8. The article of claim 7 wherein the zinc dibenzylthiocarbamate is present in a concentration range of about 0.4 parts per 100 parts of polyisoprene.



9. The article of claim 1 wherein the second compound containing xanthogen is present in the article in a concentration range of between about 1.0 and about 2.0 parts per 100 parts of polyisoprene.

10. The article of claim 9 wherein the second compound containing xanthogen is present in the article at a concentration of about 1.5 parts per 100 parts of polyisoprene.

11. The article of claim 1, wherein said article is a condom.

12. The article of claim 11, wherein said condom is a continuous, defect-free film.